

ASA-X_{@df}

ASA-X @df is our highly modified “industrial-grade” ASA filament with many features like UV resistance, zero warp technology and excellent mechanical properties. ASA-X is the perfect replacement when you require a performance material without the problems that can arise during printing with, for example, ABS. ASA-X not only has great strength and interlayer adhesion but also features one of the best aesthetics possible with FDM 3D printing. The reliable bed adhesion will ensure a smooth printing experience. ASA-X is perfect when you are looking for beautiful and strong prints that also last outside.

Features:

- UV / Weather resistant
- Zero warp technology
- Excellent interlayer adhesion
- Great strength & aesthetics
- Reliable bed adhesion (Glass, tape & other adhesives)



Colours:

ASA-X @df is available from stock in 7 industrial colours. Other colours on request



Packaging:

ASA-X @df is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

Filament specs.

Size	∅ tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,11 g/cc
MFR 260°C/5 kg	ISO 1133	45 gr/10 min
Tensile strength at yield	ISO 527	47,5 Mpa
strain at break	ISO 527	15%
Tensile modulus	ISO 527	2020 Mpa
Impact strength - Charpy notched 23°C	ISO 179	18 kJ/m ²
Printing temp.	DF	235-255°C
Melting temp.	ISO 294	230°C ± 10°C
Vicat softening temperature	ISO 306	98°C

Additional info:

Recommended temperature for heated bed is ± 80-90°C.

ASA-X @df is printed at high temperatures to make the final product extra strong.

ASA-X @df can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C). This enhances the shelf life significantly.